



Shenzhen xingtong wireless technology co.,Ltd
Telephone: +86-755- 27850514 Fax: +86- 0755-27850514
Address: 3/F, Building A1, Qiangrongdong Industrial Zone,
Jiuwei, Xixiang, Baoan District, Shenzhen

Product specification

Product number: Tea PRO

Product name: Tea PRO BT ANT

Product item number: 20240605-001A

Producer	Audit	Date
Huangjiajun	Wu Yanlong	2024-06-05

 Shenzhen Xingtong Wieress Technology Co., Ltd		Date	2024-06-05
		Version	A0
		File number	XT-YF-004
Product model	Tea PRO BT-ANT	Product number	Tea PRO APP-RA

1.Product Constrution


- 1.Antenna material: FPC
- 2.Adhesive model: 3M-300LE
- 3.Antenna size: 29.75mm * 14.70mm * 0.2mm (length and width tolerance $\pm 0.1\text{mm}$, thickness tolerance $\pm 0.02\text{mm}$)
- 4.Coaxial dimension: 28 $\varnothing$ 0.81 second-generation IPEX (tolerance $\pm 1.0\text{mm}$)

2.Parameter index


- Scope of use: Customer supplied machines
- Antenna frequency: 2.4G (2402-2480MHz)
- Antenna impedance: 50 Ω
- Antenna standing wave:<2.3
- Return loss:<-8 dB
- Polarization mode: vertical/horizontal
- Power capacity: 5W
- Installation method: Connect the terminal wire to the motherboard

3.S11 value of antenna (S11)

- 3.1: Antenna standing wave ratio -2.4G



- 3.2: Antenna return loss value -2.4G





Shenzhen Xingtong Wieress Technology Co., Ltd

Date

2024-06-05

Version

A0

File number

XT-YF-004

Product model


Tea PRO BT-ANT

Product
number

Tea PRO APP-RA

4.Antenna performance (OTA)

■ 4.1: Antenna matching suggestions




Antenna	
Element	Value
L1 (0201)	
L2 (0201)	
L3 (0201)	
L4 (0201)	
匹配无修改	

■ 4.2: Antenna efficiency gain (testing instruments: network analyzer, oscilloscope, customer supplied engineering prototype, various standard cards, etc.)

4.2.1: 2.4G-2D

Frequency ID	1	2	3	4	5	6	7	8	9	10	11
Frequency (MHz)	2400.0	2410.0	2420.0	2430.0	2440.0	2450.0	2460.0	2470.0	2480.0	2490.0	2500.0
Efficiency (dBi)	-6.39	-6.47	-6.37	-6.37	-6.55	-6.23	-6.28	-6.42	-6.04	-6.17	-6.23
Gain (dBi)	1.37	1.36	1.49	1.47	1.29	1.66	1.69	1.53	1.93	1.63	1.47
Efficiency (%)	22.98	22.54	23.08	23.06	22.13	23.81	23.56	22.79	24.88	24.18	23.82
Directivity (dB)	7.76	7.83	7.86	7.84	7.84	7.89	7.97	7.96	7.97	7.80	7.70
Peak Gain Position (Theta)	165.00	165.00	165.00	165.00	165.00	165.00	165.00	165.00	165.00	165.00	165.00
Peak Gain Position (Phi)	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Efficiency ThetaPol (%)	12.91	12.66	13.04	13.12	12.55	13.39	13.18	12.85	13.93	13.46	13.33
Efficiency PhiPol (%)	10.07	9.88	10.04	9.94	9.58	10.42	10.38	9.94	10.95	10.72	10.49
Upper Hem. Efficiency (%)	8.99	8.83	9.11	9.13	8.76	9.37	9.18	8.83	9.60	9.31	9.17
Lower Hem. Efficiency (%)	13.99	13.71	13.97	13.94	13.37	14.44	14.38	13.96	15.29	14.87	14.65


4.2.1: 2.4G-3D



 Shenzhen Xingtong Wieress Technology Co., Ltd		Date	2024-06-05
		Version	A0
		File number	XT-YF-004
Product model	Tea PRO BT-ANT	Product number	Tea PRO APP-RA

5. Attached image:

5.1: Antenna finished product diagram



 Shenzhen Xingtong Wieress Technology Co., Ltd		Date	2024-06-05
		Version	A0
		File number	XT-YF-004
Product model	Tea PRO BT-ANT	Product number	Tea PRO APP-RA

7. Reliability test:

Serialnumber	test item	Test requirements	testing tool	test result
1	Resistance to tin melting	288℃, 10S, no delamination, no foaming	Tin furnace	Ok
2	weldability	245℃, 5s, smooth tin surface, solder surface≥95%	Tin furnace	Ok
3	Pulling force	N/A	tautness meter	Ok
4	Reverse pulling force	N/A	tautness meter	Ok
5	Peel strength (covering film)	≥0.35kg/cm	peel strength	Ok
6	Peel strength (copper foil)	≥0.8kg/cm	peel strength	Ok
7	Hot melt adhesive fluidity	0.1~0.15	/	Ok

7. Matters needing attention:

After opening, please carefully check whether the goods are complete. If there is any damage, please contact us immediately.