

產品規格承認書

Specification For Approval

日期：2005 / 03 / 04

Date

編號：STA - 0789

File No.

承認廠商：友勁科技股份有限公司

Customer

製造廠商：英碩企業股份有限公司

Manufacturer

型號品名：SMA 90 ° Type(母頭公針)

Part Number

Description

INVAX P/N : CR-RSPRF5A2727B

廠商審核：

Approved By

Invax

英碩企業股份有限公司

台北市忠孝東路五段 815 號 4 樓

Tel: (02)2788-5218 Fax: (02)2783-1658

Web Site: www.invax.com.tw

E-mail: info@invax.com.tw

MTC38668

- 一、測試項目：分光分析（鋅合金）
二、使用設備：Fisons ARL 3460 Optical Emission Spectrometer 分光儀
三、測試方法：ASTM E-2 SM 6-15 (92)
四、測試環境：溫度 23°C
五、測試結果：

編號	Composition (%)						
	鋅 Zn	鐵 Fe	鋁 Al	鎂 Mg	銅 Cu	鉛 Pb	錫 Sn
鋅合金 3F	95.70	<0.001	3.84	0.029	0.40	0.002	0.002

註：<小於表示分析能力超過範圍。



金 全 福 企 業 有 限 公 司
JCF CHUAN FUH ENT.CO./LTD.

鋅合金

3F

—以下空白—

Handwritten signature and date: 27/2/02





化學實驗室委託試驗報告表

委託者	金全福企業有限公司
報告編號	MTC38669
工令單號	L93SE000-3775
金試字號	93.0063
取樣者	—
樣品名稱	鋅合金3F
工程名稱	—
來樣日期	2004/11/30
發發日期	2004/12/05

本報告含附頁共 2 頁。

羅家軒

張奇明

報告簽署人 (Report Authorized Person)

檢驗員 (Inspector)

- 注意
1. 送檢樣品經實驗室測試結果如附頁。
 2. 本報告僅對送檢樣品負責。
 3. 本報告未經書面許可不得複製或轉錄。
 4. 本報告分發使用無效。

金屬工業研究發展中心

高雄市楠梓區811高楠公路1001號

宮前五金股份有限公司

檢驗報告表

編號: 881130

88年11月25日

客 戶		康碩電子廠		
品 名		FREE CUTTING BRASS ROD		丸2.0 m/m
規 格		JIS H3250 C3604 BD		
項 目	數 據	標 準 值	實 測 值	備 註
化 學 成 份 %	Cu	57.0-61.0	59.18	康碩電子有限公司 2003 9. 11 工 程 部 發 文
	Pb	1.8 - 3.7	2.97	
	Fe	< 0.5	-----	
	Sn+Fe	< 1.2	0.71	
	Zn	REMAINDER	REMAINDER	
其 它				

App Name :

數據	μ in Au	日期 / 時間
1	5.68	2003/8/26 01:14
2	5.43	2003/8/26 01:15
3	5.73	2003/8/26 01:15
4	6.06	2003/8/26 01:16
5	5.34	2003/8/26 01:16

康碩電子有限公司
2003 9. 11
工程部發文

TO: 康碩
貴司物料: SMA 針芯
經 X-RAY 膜厚測試儀測試,
鍍層厚度已符合貴司要求.

測試員	雷華友
審核	李聯英
確認	江玲子

App Name :

數據	μ in Au	日期 / 時間
1	1.38	2003/9/7 13:10
2	1.42	2003/9/7 13:11
3	1.50	2003/9/7 13:12
4	1.39	2003/9/7 13:12
5	1.48	2003/9/7 13:13

康碩電子有限公司
 2003.9.11
 工程部發文

TO: 康碩
 貴司物料: SMA 外殼,
 經 X-RAY 膜厚測試儀測試,
 鍍層厚度已符合貴司要求:

測試員	禹華友
審核	李群英
確認	

各種充てん材入りPTFEの特性

単 位	測定条件	充てん材 (重量%)	純PTFE	ガラスファイバー15%	ガラスファイバー20%	ガラスファイバー25%	グラファイト15%
				G15	G20	G25	GR15
比 重	g/cm ³	25°C	2.17	2.23	2.24	2.26	2.16
熱 伝 導 率	kcal/m-hr·°C		0.20	0.29	0.30	0.34	0.34
熱 膨 脹 係 数	25~100°C	MD	11	11	10	9	10
		CD	10	8	7	6	8
	25~150°C	MD	12	12	11	10	11
		CD	11	8	8	7	9
	25~200°C	MD	14	13	12	11	12
		CD	12	9	9	7	9
	25~250°C	MD	17	14	13	13	14
		CD	16	10	10	9	11
引 張 強 さ	kgf/cm ²	JISK6891	330	290	234	220	200
伸 び	%	JISK6891	350	340	338	310	325
圧 縮 強 さ	0.2%オフセット 24°C	MD	—	—	85	—	—
		CD	73	74	76	80	100
	1%変形 24°C	MD	—	—	63	—	—
		CD	44	50	60	80	70
	25%変形 24°C	MD	—	—	254	—	—
		CD	280	280	283	290	300
圧 縮 弾 性 率	kgf/cm ²	MD	—	—	—	—	—
曲 げ 強 さ (弾性率)	kgf/cm ²	CD	5.7×10 ³	8.8×10 ³	9.6×10 ³	10.6×10 ³	7.8×10 ³
		ASTMD-790	3.5~ 6.3×10 ³	21.8×10 ³	19.0×10 ³	16.7×10 ³	—
圧 縮 ク リ ー プ 1. 変 形 率	ASTMD-621 140kgf/cm ² 25°C 24hrs 2	MD	9.5	8.8	8.5	7.9	5.0
		CD	—	—	—	—	—
	70kgf/cm ² 25°C・24hrs	MD	4.8	4.4	3.6	3.5	3.1
		CD	—	—	—	—	—
2. 永 久 変 形	140kgf/cm ² 25°C・24hrs	MD	7.0	6.9	6.7	6.2	3.8
		CD	—	—	11.5	—	—
	70kgf/cm ² 25°C・24hrs	MD	4.6	3.8	3.5	3.3	3.0
		CD	—	—	—	—	—
硬 度	ショア-D		58	58	59	60	58
摩 擦 係 数 (動)			0.22	0.24	0.24	0.26	0.23
摩 擦 係 数 (静)			0.045	0.065	0.073	0.085	0.058
摩 耗 係 数	mm/km kgf/cm ²	65hrs鈴木式 試験機による	2×10 ⁻²	1.2×10 ⁻⁵	1.1×10 ⁻⁵	1.0×10 ⁻⁵	6.7×10 ⁻⁵
絶 縁 耐 力	kv/mm	JISD2120(油中)	46.4	17.4	15.5	13.7	4.1
誘 電 率	JISD6911	10 ³ Hz	2.06	2.64	2.91	2.94	—
		10 ⁶ Hz	2.06	2.80	2.77	2.89	—
吸 水 率	%	3.2mmt24H ASTM D570	0.01>	0.015	0.014	0.013	0

※MDは成形加工に平行方向、CDは成形加工に直角方向

※この表はフッ素樹脂メーカーのデータ等を基にした数値も含まれます。

数値は、ある一定環境において行われた実験データで、環境の違いにより若干異なることがあります。(規格値ではありません)

康碩電子有限公司

2003.9.11

工 程 部 發 文



Test Report

INVAX SYSTEM & TRADING CORP.
CORTEC TECHNOLOGY INC.
4F, No.815, CHUNG HSAIO EAST RD. SEC.5,
TAIPEI, TAIWAN, R.O.C.

Report No. : CE/2004/C1640A
Date : 2004/12/16
Page : 1 of 5


The following merchandise was (were) submitted and identified by the client as :

Type of Product : ANTENNA
Style/Item No. : EM SERIES; IM SERIES; NB SERIES; AN SERIES
Sample Received : 2004/01/05 & 2004/04/23 & 2004/06/11 & 2004/06/24 &
2004/12/09 & 2005/01/26
Testing Date : 2004/01/05 TO 2004/01/06 & 2004/04/23 TO 2004/04/28 &
2004/06/11 TO 2004/06/21 & 2004/06/24 TO 2004/07/01 &
2004/12/09 TO 2004/12/16 & 2005/01/26 TO 2005/01/28

=====

Test Result : - Please see the next page -

*This report is combined with reports of SZTYR050102512/LP & CE/2004/62767 &
GZSCR040100230/LP & CE/2004/61520 & GZSCR040413274/LP*


Daniel Yen, M.R. / Operation Manager
Signed for and on behalf of
SGS TAIWAN LTD.

The content of this PDF file is in accordance with the original issued reports for reference only. This Test Report cannot be reproduced, except in full, without prior written permission of the Company



Test Report

INVAX SYSTEM & TRADING CORP.
CORTEC TECHNOLOGY INC.
4F. No.815, CHUNG HSAIO EAST RD. SEC.5,
TAIPEI, TAIWAN, R.O.C.

Report No. : CE/2004/C1640A
Date : 2004/12/16
Page : 2 of 5

Test Result

PART NAME NO.1 : BRASSY COLOR METAL BAR(SZTYR050102512/LP)
PART NAME NO.2 : BLACK PLASTIC SHEET(GZSCR040100230/LP)
PART NAME NO.3 : TAN TRANSPARENT LIQUID(GZSCR040413274/LP)
PART NAME NO.4 : BLACK PLASTIC JACKET(KHCX-32AWG-SB-TA)(CE/2004/61520)
PART NAME NO.5 : TRANSPARENT FEP JACKET(CE/2004/C1640)
PART NAME NO.6 : WHITE PALSTIC(CE/2004/62767)

Test Item (s):	Unit	Method	MDL	Result				
				No.1	No.2	No.3	No.4	No.5
PBBs(Polybrominated biphenyls)(CAS NO:059536-65-1)	%	With reference to USEPA3540C or USEPA3550C. Analysis was performed by HPLC/DAD, LC/MS or GC/MS. (prohibited by 2002/95/EC (RoHS), 83/264/EEC, and 76/769/EEC)	0.0005	---	---	---	N.D.	N.D.
PBBs(PBDEs)(Polybrominated biphenyl ethers)	%	With reference to USEPA3540C or USEPA3550C. Analysis was performed by HPLC/DAD, LC/MS or GC/MS. (prohibited by 2002/95/EC (RoHS), 83/264/EEC, and 76/769/EEC)	0.0005	---	---	---	N.D.	N.D.

Test Item (s):	Unit	Method	MDL	Result				
				No.1	No.2	No.3	No.4	No.5
Chromium VI (Cr+6)	ppm	As per US EPA 7196A and US EPA 3060A.	2	N.D.	---	N.D.	N.D.	N.D.
Cadmium (Cd)	ppm	ICP-AES after as per EN 1122, method B:2001 or other acid digestion.	2	22.0	N.D.	N.D.	N.D.	N.D.

The content of this PDF file is in accordance with the original issued reports for reference only. This Test Report cannot be reproduced, except in full, without prior written permission of the Company



Test Report

INVAX SYSTEM & TRADING CORP.
CORTEC TECHNOLOGY INC.
4F. No.815, CHUNG HSAIO EAST RD. SEC.5,
TAIPEI, TAIWAN, R.O.C.

Report No. : CE/2004/C1640A
Date : 2004/12/16
Page : 3 of 5

Test Item (s):	Unit	Method	MDL	Result				
				No.1	No.2	No.3	No.4	No.5
Lead (Pb)	ppm	ICP-AES after as per US EPA 3050B or other acid digestion.	2	24600.0	6.0	N.D.	N.D.	N.D.
Mercury (Hg)	ppm	ICP-AES after as per US EPA 3052 or other acid digestion.	2	N.D.	---	N.D.	N.D.	N.D.

Test Item (s):	Unit	Method	MDL	Result
				No.6
AZO		As per LMBG 8202-2		
4-AMINODIPHENYL (CAS NO.92-67-1)	ppm	Analysis was performed by GC/MS.	3	N.D.
BENZIDINE (CAS NO.92-87-5)	ppm	Analysis was performed by GC/MS.	3	N.D.
4-CHLORO-O-TOLUIDINE (CAS NO.95-69-2)	ppm	Analysis was performed by GC/MS.	3	N.D.
2-NAPHTHYLAMINE (CAS NO.91-59-8)	ppm	Analysis was performed by GC/MS.	3	N.D.
O-AMINOAZOTOLUENE (CAS NO.97-56-3)	ppm	Analysis was performed by GC/MS.	3	N.D.
2-AMINO-4-NITROTOLUENE (CAS NO.106-47-8)	ppm	Analysis was performed by GC/MS.	3	N.D.
2,4-DIAMINOANISOLE (CAS NO.615-05-4)	ppm	Analysis was performed by GC/MS.	3	N.D.
4,4-DIAMINODIPHENYLMETHANE (CAS NO.101-77-9)	ppm	Analysis was performed by GC/MS.	3	N.D.
3,3-DICHLOROBENZIDINE (CAS NO.91-94-1)	ppm	Analysis was performed by GC/MS.	3	N.D.
3,3-DIMETHOXYBENZIDINE (CAS NO.119-90-4)	ppm	Analysis was performed by GC/MS.	3	N.D.
3,3-DIMETHYLBENZIDINE (CAS NO.119-93-7)	ppm	Analysis was performed by GC/MS.	3	N.D.

The content of this PDF file is in accordance with the original issued reports for reference only. This Test Report cannot be reproduced, except in full, without prior written permission of the Company.



Test Report

INVAX SYSTEM & TRADING CORP.
CORTEC TECHNOLOGY INC.
4F, No.815, CHUNG HSAIO EAST RD. SEC.5,
TAIPEI, TAIWAN, R.O.C.

Report No. : CE/2004/C1640A
Date : 2004/12/16
Page : 4 of 5

Test Item (s):	Unit	Method	MDL	Result
				No.6
3,3-DIMETHYL-4,4-DIAMINODIPHENYLMETHANE (CAS NO.838-88-0)	ppm	Analysis was performed by GC/MS.	3	N.D.
P-CRESIDINE(2-METHOXY-5-METHYLANILINE) (CAS NO.120-71-8)	ppm	Analysis was performed by GC/MS.	3	N.D.
4,4-METHYLENE-BIS-(2-CHLORANILINE) (CAS NO.101-14-4)	ppm	Analysis was performed by GC/MS.	3	N.D.
4,4-OXYDIANILINE (CAS NO.101-80-4)	ppm	Analysis was performed by GC/MS.	3	N.D.
4,4-THIODIANILINE (CAS NO.139-65-1)	ppm	Analysis was performed by GC/MS.	3	N.D.
O-TOLUIDINE (CAS NO.95-53-4)	ppm	Analysis was performed by GC/MS.	3	N.D.
2,4-TOLUYLENDIAMINE (CAS NO.95-80-7)	ppm	Analysis was performed by GC/MS.	3	N.D.
2,4,5-TRIMETHYLANILINE (CAS NO.137-17-7)	ppm	Analysis was performed by GC/MS.	3	N.D.
O-ANISIDINE (CAS NO.90-04-0)	ppm	Analysis was performed by GC/MS.	3	N.D.
P-AMINOAZOBENZENE (CAS NO.60-09-3)	ppm	Analysis was performed by GC/MS.	3	N.D.

Test Item (s):	Unit	Method	MDL	Result
				No.6
Mirex(CAS NO:002385-85-5)	ppm	Analysis was performed by GC/MS.	4	N.D.

Test Item (s):	Unit	Method	MDL	Result
				No.6
PCBs(Polychlorinated Biphenyls)(CAS NO:001336-36-3)	ppm	With reference to USEPA 8082A. Analysis was performed by GC/ECD/MS.	0.5	N.D.

The content of this PDF file is in accordance with the original issued reports for reference only. This Test Report cannot be reproduced, except in full, without prior written permission of the Company



Test Report

INVAX SYSTEM & TRADING CORP.
CORTEC TECHNOLOGY INC.
4F. No.815, CHUNG HSAIO EAST RD. SEC.5,
TAIPEI, TAIWAN, R.O.C.

Report No. : CE/2004/C1640A
Date : 2004/12/16
Page : 5 of 5

Test Item (s):	Unit	Method	MDL	Result
				No.6
PBBs(Polybrominated biphenyls)(CAS NO:059536-65-1)	%	With reference to USEPA3540C or USEPA3550C. Analysis was performed by HPLC/DAD, LC/MS or GC/MS. (prohibited by 2002/95/EC (RoHS), 83/264/EEC, and 76/769/EEC)	0.0005	N.D.
PBBs(PBDEs)(Polybrominated biphenyl ethers)	%	With reference to USEPA3540C or USEPA3550C. Analysis was performed by HPLC/DAD, LC/MS or GC/MS. (prohibited by 2002/95/EC (RoHS), 83/264/EEC, and 76/769/EEC)	0.0005	N.D.

Test Item (s):	Unit	Method	MDL	Result
				No.6
Cadmium (Cd)	ppm	ICP-AES after as per EN 1122, method B:2001 or other acid digestion.	2	N.D.
Lead (Pb)	ppm	ICP-AES after as per US EPA 3050B or other acid digestion.	2	N.D.

- NOTE: (1) N.D. = Not detected (<MDL)
(2) ppm = mg/kg
(3) MDL = Method Detection Limit
(4) " --- " = Not Applicable
(5) " - " = No Regulation
(6) * = Results shown are of the adjusted analytical results
(7) ** = Qualitative analysis (No Unit)
(8) Negative = Undetectable / Positive = Detectable
(9) The MDL is 5ppm for the single compound of CP

The content of this PDF file is in accordance with the original issued reports for reference only. This Test Report cannot be reproduced, except in full, without prior written permission of the Company