

Print this Page

**Fasson® 2 Mil Matte Chrome Polyester TC/S730/50# SCK
ABC****Spec# 41044****Facestock:**

Fasson® 2 Mil Matte Chrome Polyester TC is a matte finished metallic film featuring excellent tear strength, heat resistance, dimensional stability, opacity and chemical resistance. Designed for printing with most solvent and some water-based flexographic inks. Suitable for thermal transfer printing applications with select thermal transfer ribbons. Specific testing required.

Basis Weight:	
Caliper:	0.002 inches $\pm$ 10%
Tensile:	MD 18,000 psi CD 18,000 psi
Tear:	
Stiffness:	

Adhesive:

Fasson® S730 adhesive is a clear adhesive featuring good initial tack, high shear, minimal cold flow and ultimate adhesion to a wide variety of substrates.

Type:	Solvent Acrylic
Minimum Application Temperature:	+45° F
Service Temperature Range:	-40° F to +300° F subject to facestock limitations

Typical Performance Data: 2 Mil Clear Polyester at room temperature on standard lab panels**Stainless Steel**

Loop Tack:	2.1 lbs
Peel Adhesion:	4.2 lbs

Aluminum

Loop Tack:	N/A
Peel Adhesion:	5.4 lbs

Alkyd Enamel Paint

Loop Tack:	N/A
Peel Adhesion:	3.9 lbs

Polypropylene

Loop Tack:	N/A
Peel Adhesion:	1.7 lbs

HDPE

Loop Tack:	N/A
Peel Adhesion:	0.7 lbs

Liner:

50# SCK is a bleached, super calendered paper stock with very good diecutting and matrix stripping properties. Supplied with an Anti Block Coating on the backside of the liner to control adhesive and label transfer to the backside of the liner in finished, wound rolls. This liner should not be used in fanfolded label applications and is not recommended for back printability.

Basis Weight:	53.5# per ream $\pm$ 10% (24" X 36" 500 sheets)
Caliper:	0.0032 inches $\pm$ 10%
Tensile:	MD 45# per inch width CD 24# per inch width
Tear:	MD 48 grams

Print this Page

**Fasson® 2 Mil Clear Printable Polyester/S730/50# SCK
ABC****Spec# 61319****Facestock:**

Fasson® 2 Mil Clear Printable Polyester is a highly transparent film featuring excellent tear strength, heat resistance, dimensional stability and chemical resistance. Designed to enhance printability with solvent and water-based flexographic ink systems. Also provides enhanced UV letterpress printability. Suitable for thermal transfer printing applications with select ribbons. Specific testing required.

Basis Weight:	2 Mil Clear Printable Polyester
Caliper:	0.002 inches $\pm$ 10%
Tensile:	MD 33,500 psi CD 33,500 psi
Tear:	n/a
Stiffness:	n/a

Adhesive:

Fasson® S730 adhesive is a clear adhesive featuring good initial tack, high shear, minimal cold flow and ultimate adhesion to a wide variety of substrates.

Type:	Solvent Acrylic
Minimum Application Temperature:	+45° F
Service Temperature Range:	-40° F to +300° F subject to facestock limitations

Typical Performance Data: 2 Mil Clear Polyester at room temperature on standard lab panels

Stainless Steel

Loop Tack:	2.1 lbs
Peel Adhesion:	4.2 lbs

Aluminum

Loop Tack:	N/A
Peel Adhesion:	5.4 lbs

Alkyd Enamel Paint

Loop Tack:	N/A
Peel Adhesion:	3.9 lbs

Polypropylene

Loop Tack:	N/A
Peel Adhesion:	1.7 lbs

HDPE

Loop Tack:	N/A
Peel Adhesion:	0.7 lbs

Liner:

50# SCK is a bleached, super calendered paper stock with very good diecutting and matrix stripping properties. Supplied with an Anti Block Coating (ABC) on the backside of the liner. ABC controls adhesive and label transfer to the backside of the liner in finished, wound rolls. This liner should not be used in fanfolded label applications, and is not recommended for back printability.

Basis Weight:	54# per ream $\pm$ 10% (24"x36" 500 sheets)
Caliper:	0.0032 inches $\pm$ 10%
Tensile:	MD 48# per inch width CD 26# per inch width
Tear:	MD 50 grams