




TOP




SIDE 1



SIDE 2



LABEL APPLICATION




REVISION HISTORY			
REV	DESCRIPTION	DATE	APPROVED
A	INITIAL APPROVAL;	09-01-23	J.KUEHL J.BRUNO

NOTES:

- RAW LABEL: 235392
- MATERIAL: WHITE POLYESTER WITH CLEAR POLYESTER COMPUTER IMPRINTABLE OVERLAMINATE
- LABEL COLOR: MATTE BLACK
- LETTERING & IMAGES MUST NOT BE TOUCHING EDGE OF LABEL NOR BE CUT OFF.
- MAXIMUM IMAGE DEVIATION FROM ARTWORK: ±.05mm

SEE SHEET 2 FOR LABEL CROSS REFERENCES

DIMENSIONS ARE IN MILLIMETERS UNLESS OTHERWISE SPECIFIED TOLERANCE ON ANGLE: ±3° X ±0.5 X.X ±0.3 X.XX ±0.15 INTERPRET DIMENSIONS & TOLERANCES PER ASME Y14.5M - 2009				ALL SHEETS ARE THE SAME REVISION STATUS			
THIRD ANGLE PROJECTION 		This drawing is the property of BANNER ENGINEERING CORP. and is proprietary in general and in detail. Its contents shall not be revealed to outside parties without written consent of BANNER.		BANNER ENGINEERING CORP. P.O. BOX 9414 MINNEAPOLIS, MN 55440			
		DRAWN BY J. KUEHL	DATE 09-01-23	TITLE LABEL PROGRAM Q90R			
		APPROVED BY J. BRUNO	DATE 09-0123	SIZE B	DRAWING NO. 237086	REV. A	
		APPROVED BY	DATE	SCALE 2:1	SHEET 1 OF 2		



Durable Goods and Equipment Labeling

Clear Gloss Polyester Overlamine

End Use Applications:

Compliance Labels
Warning & Instructional Labels
Nameplates
Brand Identity Labels

For Durable Goods including:

Outdoor Power Equipment
Power Tools
Appliances
Electronics
Recreational Vehicles
Sporting Equipment
Industrial Equipment...and more

For Transportation including:

Automotive
Aerospace
Heavy Equipment

For more information on FLEXcon's pressure-sensitive film solutions for Durable Goods and Equipment Labeling, contact your local Sales Representative or our Product Identification Business Team at (508) 885-8300.

Product ID #: FLX000464



This image is an example of how FLEXcon products may be used

Product:

THERMLfilm SELECT® 10852

Benefits:

- 1.0 mil clear polyester film provides excellent clarity and label protection
- Overlaminating polyester resists temperature extremes, abrasion and chemical exposure for maximum label protection
- Topcoat resists smudging and abrasion when printed with resin and wax/resin thermal transfer ribbons
- Permanent, pressure-sensitive acrylic bonds well to base film label substrates
- Overlaminating adhesive offers excellent wetout and clarity
- Backed with a 44 lb. polycoated natural Kraft release liner ideal for roll-form converting
- Smooth, polycoated release liner provides good adhesive wetout for clarity of graphics
- UL recognized under UL 969 - UL File No. PGJ12.MH16635 Printing Materials - Component
- CSA accepted with specific thermal transfer ribbon(s) and printer(s) under CSA standard C22.2 No. 0.15-95



THERMLfilm SELECT® 10852

PRODUCT DATA	VALUE	TEST METHOD
Physical Properties		
Thickness (Mils[microns])	Film 1.0 (25) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
	Adhesive 0.8-0.9 (20-23) +/- 0.1 (3)	
	Liner 3.0 (76) +/- 10%	
Dimensional Stability (%)	No Shrinkage Observed	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties		
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In (N/m)	
Acrylic	45 (495)	
Glass	29 (319)	
Polypropylene	5 (55)	
Stainless Steel	34 (374)	ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Expected Shear		
Room Temp (hours)	25	
Tack (gm/sq cm)	320	ASTM D 2979
Expected Exterior Life	Two years	
Service Temperature Range	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 11/20/2015



Product Construction Sheet

FLX019450 - FLEXcon® FLEXmark® PM 200 WHITE TC-245 L-23 SPEC 50K-7

GENERAL DESCRIPTION:

This is a topcoated white polyester film coated with a permanent pressure sensitive acrylic adhesive and backed with semi-bleached kraft release liner.

UL/CSA RECOGNITION:

This product is UL recognized. For further information, please reference FLEXcon's UL file number PGGU2.MH10170 and CSA file # 099214-L-000 class 7922-01 or contact your FLEXcon representative.

PRODUCT DATA	VALUE	TEST METHOD
PHYSICAL PROPERTIES		
Thickness	Film: 2.0 (51) +/- 10 %	ASTM D 3652 (Modified for use with non-tape product)
mil (micron)	Adhesive: 0.8-0.9 (20-23) +/- 0.1 (3)	
	Liner: 3.1 (79) +/- 10 %	
Dimensional Stability (%)	No shrinkage observed	On Al panel at 160°F (71°C) for 24 hr.

ADHESION PROPERTIES*

Adhesion from	Average oz/in (N/m)	
Stainless Steel	55 (605)	ASTM D 903 (Modified for 72 hr dwell time)
Acrylic	65 (715)	
Glass	63 (693)	
Polypropylene	6 (66)	
Expected Shear (hours)	50	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (gm)	1050	ASTM D 2979

* For guidance only, not to be used for setting specifications. Due to the custom nature of this product, the data presented are based on three or less production runs.

EXPECTED EXTERIOR LIFE	Two years
SERVICE TEMPERATURE RANGE	-40°F to 302°F (-40°C to 150°C)
MINIMUM APPLICATION TEMPERATURE	50°F (10°C)
STORAGE STABILITY	Two years stored at 70°F (21°C) and 50% RH
FLEXmark is a registered trademark of FLEXcon Company, Inc.	
09/16/2013	

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.